

**SPP7**

The 7<sup>th</sup> International Conference on  
**Surface Plasmon Photonics**  
 May 31 – June 5, 2015 | Jerusalem, Israel

### Optimization of Plasmonic Structure Integrated Single-Photon Detector Designs

Mária Csete<sup>1</sup>, Gábor Szekeres<sup>1</sup>, Balázs Bánhelyi<sup>2</sup>, András Szenes<sup>1</sup>, Tibor Csenedes<sup>2</sup>, Gábor Szabó<sup>1</sup>


<sup>1</sup> Department of Optics and Quantum Electronics, University of Szeged, Szeged, Hungary

<sup>2</sup> Department of Computational Optimization, University of Szeged, Szeged, Hungary

Superconducting nanowire single photon detectors (SNSPD) are devices to detect infrared light up to single-photon resolution with high speed. Plasmonic structures integrated into SNSPDs are capable of enhancing absorptance along with the reduction of kinetic inductance. Nano-cavity-array (NCAI), nanocavity-deflector-array (NCDAI) and nano-cavity-double-deflector-array (NCDDAI) were integrated around meandered pattern of 4 nm thick niobium-nitride (NbN) superconducting stripes [1, 2]. To find the optimal plasmonic structure integrated SNSPD configurations resulting in maximal NbN absorptance for p-polarized 1550 nm light illumination the built in algorithms of COMSOL were used, and all geometrical parameters as well as the illumination direction were varied.

The highest p-polarized absorptance was achieved in S-orientation ( $\gamma=90^\circ$  azimuthal angle) of all integrated SNSPDs. The highest 94.2% absorptance was attained in half-wavelength-scaled periodic NCAI-SNSPD at  $76.4^\circ$  tilting corresponding to the plasmonic Brewster angle. In half-wavelength-scaled NCDAI-SNSPD plasmonic pass bands appeared, and the highest 94.6% absorptance was attained at  $50.7^\circ$  tilting due to reflectance suppression. In NCDDAI-SNSPD three-quarter-wavelength-scaled pattern results in the largest 92.9% absorptance at  $18.9^\circ$  tilting due to first-order grating coupling.

In the optimized configurations the spectral sensitivity and dispersion characteristics were investigated of all integrated SNSPD devices. The optical response for s-polarized light illumination was also inspected, and the achievable polarization contrast was determined. Finally the illumination direction and spectral sensitivity of the polarization contrast was examined, which is a crucial property of SNSPDs in quantum communication and cryptography. In conclusion: half-wavelength-scaled deflector arrays promote to reach larger absorptance, while three-quarter-wavelength-scaled double deflectors make possible to enhance polarization contrast considerably.



(a) NbN absorptance and polarization contrast as a function of  $\phi$  polar angle in integrated SNSPDs optimized by COMSOL. Dispersion relation of the optimized (b) NCAI-, (c) NCDAI- and (d) NCDDAI-SNSPD. Time-averaged  $\mathbf{E}$ -field with power-flow arrows at maxima are depicted as insets.

[1] M. Csete, A. Szalai, Á. Sipos, G. Szabó: Optics Express **20**/15, 17065-17081 (2012)

[2] M. Csete, Á. Sipos, A. Szalai, F. Najafi, G. Szabó. K.K. Berggren: Scientific Reports **3**:2406 (2012)

mcsete@physx.u-szeged.hu

Close